



LANIFICIO
dell' OLIVO
Italian Fancy Yarns

Movida

NM.34000

70% VISCOSA 21% FIBRA METALLIZZATA 9% POLIESTERE

70% VISCOSE 21%METALLIZED FIBRE 9% POLYESTER

IMPIEGO

AD UN CAPO SU MACCHINE RETTILINEE F. 14

NORMATIVE E CAPITOLATI

♦Il filato è prodotto in conformità con il regolamento europeo **REACH**. Per i colori della cartella, dopo un lavaggio industriale in acqua il filato è conforme alla normativa **GB 18401:2010** (rpc) categoria b: prodotti a diretto contatto con la pelle. Metodo di analisi a singola fibra. Eventuali colori a campione dovranno essere testati.

♦ Si raccomanda di verificare che tutte le caratteristiche del filato soddisfino i requisiti richiesti dal Vostro prodotto, anche in considerazione del tipo di lavorazione da effettuare e dell'utilizzo previsto.

FINISSAGGIO INDUSTRIALE

È importante effettuare un pre-stiro prima del trattamento. Consigliamo un lavaggio in acqua a max 30°C per 2/3 minuti al fine di permettere il rientro dei teli e ridurre la presenza di formaldeide. Si consiglia di effettuare le prove di trattamento ad acqua ed a secco al fine di verificare il comportamento del proprio manufatto ai lavaggi e calcolare preventivamente il restringimento per assicurarsi la conformità delle taglie.

ISTRUZIONI DI LAVAGGIO PER LA MANUTENZIONE DEL CAPO

Lavaggio manuale con sapone neutro. Per capi rigati o con forti contrasti di colore lavare solo a secco. Si consiglia di effettuare le prove di lavaggio sul proprio manufatto e di verificare che le solidità sotto riportate siano idonee alle proprie esigenze.

SIMBOLOGIA INTERNAZIONALE DI MANUTENZIONE

CAPI UNITI // PLAIN GARMENTS



END USE

FLAT KNITTING MACHINES: ONE END ON 14 GAUGE

REGULATIONS AND LAWS

♦This yarn is produced in conformity with the european regulation **REACH**. After an industrial washing of the garments, for our own card colors the yarn is in conformity with normative **GB 18401:2010** (rpc) category b: products direct contact with skin. Single fibre test method. Any custom color has to be tested.

♦ It is recommended to verify that all the characteristics of the yarn meet the requirements of your product, also considering the type of work to be carried out and the intended use.

INDUSTRIAL FINISHING


We recommend to iron the garments before finishing them. It is necessary to make a water washing at 30°C for 2-3 minutes to make the panels shrink properly and reduce the presence of formaldehyde. We suggest to make a test to both water washing and to dry cleaning to check in advance the garment shrinkage and ensure the conformity of the size.

WASHING INSTRUCTION FOR GARMENTS END USERS

Hand washing with neutral soap. For striped garments with strong colour contrast we recommend to dry clean only. We suggest to make your own finishing trials and check that the below color fastness rates are suitable for your needs.

//GARMENT CARE INTERNATIONAL SYMBOLOGY

CAPI RIGATI // STRIPED GARMENTS



SOLIDITA COLORI

COLORFASTNESS

Solidità Color fastness	Lavaggio acqua Water washing		Lavaggio a secco Dry cleaning		Sudore acido Acid Perspiration		Sudore alcalino Alkaline Perspiration		Sfregamento secco Dry rubbing	Sfregamento umido Wet rubbing	Luce Light
normative	Iso 105-C06		Iso 105-D01		Iso 105-E04		Iso 105-E04		Iso 105-X12	Iso 105-X12	Iso 105-B02
	staining	col change	staining	col change	staining	col change	staining	col change	staining	staining	col change
Light col	4	4	4	4	3 / 4	3 / 4	3 / 4	3 / 4	4	4	2 / 3
Med col	3 / 4	4	3 / 4	4	3 / 4	3 / 4	3 / 4	3 / 4	3 / 4	3 / 4	3 / 4
Dark col	3	4	3	4	3	3 / 4	3	3 / 4	3	2 / 3	4 / 5

I dati sopra riportati sono da ritenersi valori medi per colori presenti in cartella

Above-mentioned values are average values for colors available in the color card

Tipo di tintura :	Realizzato da filati tinti	Dyeing method	Made from pre-dyed components
Tasso di ripresa convenzionale:	9,41%	Conventional regain allowance	9,41%
Controllo colore	luce del giorno D65	Quality control	daylight D65
Valore pH norma Iso 3071	da 4 a 8	pH value normative Iso 3071	4 up to 8
Peso metro quadro	110 gr	GR/Square meter	110 gr.
Tipo nodo	manuale	Knot type	hand knot

AVVERTENZE

♦Sporadiche variazioni di intensità del colore non sono eliminabili, lavorare a due o più guidafile per ottimizzare l'effetto cromatico e di struttura.

♦ Il filato è realizzato con l'impiego di fibre metallizzate speciali, è consigliabile proteggere dall'azione della luce i capi prodotti.

♦ A causa della presenza di fibra metallizzata, in alcuni lotti la quantità di formaldeide può superare i 75 ppm. Un semplice lavaggio in acqua può portare questo livello al di sotto dei 75 ppm. Per ulteriori informazioni contattare il nostro Customer Service.

♦ Possibili scarti: 5% in numero di teli. Nel caso sia riscontrato uno scarto superiore è necessario interrompere la lavorazione e contattare il nostro Customer Service. Non potrete ritenervi responsabili per ulteriori lavorazioni eseguite e capi completi realizzati.

IMPORTANTE: Durante la fase di tessitura, per non danneggiare il filato metallizzato è importante evitare punti di attrito, punti di abrasione e tensioni elevate sugli aghi e sul firahezza; può essere necessario selezionare i punti maglia e ridurre la velocità di lavoro. A causa delle caratteristiche tecnico produttive dei filati metallizzati sono possibili variazioni di colore, di mano e di scorrevolezza fra lotti diversi anche se dello stesso colore.

WARNING

♦ Sporadic variations of color intensity cannot be eliminated; please knit at two or more threadguides in order to optimize the chromatic and structural look of the garment.

♦ The yarn is made by special metallized fibers so we suggest to protect the manufactured garments from light.

♦ Due to the presence of metallic components, for some lots the quantity of formaldehyde can be higher than 75 ppm. We suggest an ordinary water washing to reduce the level of formaldehyde below 75 ppm. For further information please ask to our Customer Service.

♦ Possible wastage of panels: 5%. If the wastage is higher than 5% it is necessary to stop knitting down and contact our Customer Service. Lanificio dell'Olivo cannot be responsible for further working process and manufactured garments.

IMPORTANT: In order to avoid the breakage of the metallized filament during the knitting process, it is important to avoid friction and abrasion points and high tensions on the needles; it can be necessary to select knit stitches and reduce the knitting speed. Due to the specific technical characteristics of metallized yarns, colour variation, handfeel and slipperiness are possible between different lots, even though they are from the same color.

Tutti i dati riportati nella presente scheda tecnica sono stati ricavati da prove a campione,devono quindi ritenersi a tutti gli effetti puramente indicativi.
All above information have been checked on knitted samples and must be considered as indicative.